

AC830

INTRODUCTION

Jesmonite® AC830 is supplied as two components, a water-based acrylic liquid, and a blended base. It is formulated for external use and contains a blend of decorative aggregates and pigments to achieve a range of stone finishes. Jesmonite AC830 is a rapid setting acrylic polymer modified cementitious casting composite. It is a shrinkage-compensated material of low permeability and is durable in all conditions of external weathering. The compound is designed for fine decorative castings and is suitable for statuary, water-features, and decorative cast objects that are externally durable and frost resistant.

PREPARATION

It is essential to use both accurate scales and a Jesmonite High-Shear Mixing Blade to ensure that the compound performs within its specification. Failure to follow these instructions can lead to strength loss, shrinkage, and reduced durability. Workshop conditions should be warm, dry, and out of direct sunlight. Environments where solvent-based compounds are in regular use should be avoided. Mixing containers should be clean and dry, and of a suitable size.

MIX RATIOS

For fine decorative castings, weigh the Liquids and Base into separate clean containers at the following ratio:

Jesmonite AC830 Liquids	1 part by weight
Jesmonite AC830 Base	7 parts by weight
Jesmonite Super Plasticiser	8 – 12g/kg of mix.

MIXING

Jesmonite AC830 must be mixed using a Jesmonite High-Shear Mixing Blade. Attach this blade to a drill with variable speed control on the trigger and slowly add the Base to the Liquids whilst mixing continuously at low speed. As the last Base is added, slowly increase the mix speed to around 1,000rpm and mix for a further 60 seconds or until the mix is smooth, flowing, and free from lumps.

JESMONITE RETARDER

Jesmonite Retarder is added to the pre-weighed liquids to extend the pot-life of the mixed material. Typical inclusion rates are 2g – 8g/kg of mix, however a small test is recommended, as the precise timing is dependent on both temperature and mix size.

JESMONITE SUPER PLASTICISER

Jesmonite Super Plasticiser is added between 8–12g/kg of mix, primarily to aid ease of casting.

JESMONITE PVA FIBRES

Jesmonite PVA Fibres are added at 1–2% of the total mix weight to give both additional strength and frost resistance. N.B. We do not recommend using the Jesmonite High-shear Mixing Blade when adding the Jesmonite PVA Fibres to the mixture as the blade will break up the fibres. The Jesmonite PVA Fibres should be stirred in by hand, this will ensure that the fibres keep their shape.

SOLID CASTING

Jesmonite AC830 is designed for fine decorative castings. To reduce the chance of air bubbles at the surface of the cast, first pour a little material into the mould whilst spreading the material around with a brush. This is applied to stop the reinforcements showing on the face of the cast. The rest of the back-up mix which includes the Jesmonite PVA Fibres can now be poured, a little at a time, whilst tapping or vibrating the mould to help release any further entrained air.

CURING

Jesmonite AC830 achieves over 90% of its ultimate strength in the first 24 hours. Cast objects should be kept in a warm, dry environment during this period. They should be racked to allow optimum airflow and stored in such a way that panels cannot 'creep' or bow under their own weight. Finished products should be packaged only when cured. Care should also be taken when using plastic packaging, particularly in damp storage areas, as this can lead to surface staining and possible water marking.

SURFACE FINISH

Jesmonite AC830 is formulated to result in a stone finish. This is achieved either by acid etching, or by grit-blasting. The product can only be acid etched after curing for a minimum of 24 hours. First wet the surface of the cast with water before applying the acid solution. This will reduce the chance of the acid marking or burning the panel where it is first applied. To apply acid etch, the area must be well ventilated, and near a ready supply of clean water. The acid will produce varying degrees of etch from 1 minute through to around 4 minutes. The acid works by removing the surface to reveal the decorative aggregate and pigment in the material. The acid should be washed off with copious amounts of clean water, and the surface padded dry with a clean dry cloth. Once the surface is dry it becomes evident if there are any areas that require a further application.

STORAGE

As a basic rule liquid containers should be kept well sealed to prevent water evaporation and skin forming. They should be stored at a constant temperature between 5–25°C and used within six months. Freezing must be avoided. Base should be kept dry and stored at 5–25°C.

Jesmonite® is a Registered Trademark

The above information and recommendations are based upon our experience and are offered merely for advice. They are offered in good faith but without guarantee, as conditions and methods of use are beyond our control. It remains the responsibility of the end user to determine the suitability of the materials for the particular purpose intended.

Contact details

Jesmonite Limited
Challenge Court
Bishops Castle
Shropshire SY9 5DW
United Kingdom

Tel. +44 (0)1588 630302
Fax. +44 (0)1588 630304
www.jesmonite.com