TECHNICAL DATA SHEET (TDS100/20)

AC100

PRODUCT DESCRIPTION

Jesmonite[®] AC100 is a water-based, two-component, acrylic polymer/mineral resin system. The system is suitable for a wide range of casting and laminating applications where the end user wants to reduce the many risks associated with conventional solvent based systems. A range of ancillary products including decorative and

functional fillers, control chemicals, pigments, and glass reinforcements are also provided making the material extremely versatile. The material is suitable for internal and external use, however if used externally a sealer or suitable paint system is recommended to protect surface appearance.

SPECIFICATIONS

 Mix ratio
 2.5:1 p

 Wet density
 1845 k

 Dry density
 1745 k

 Initial set
 15 - 20

 Expansion on set
 0.15%

2.5:1 parts Base to Liquids ratio by weight 1845 kg/m³ 1745 kg/m³ 15 – 20 minutes (18°C, No Retarder) 0 15%

OTHER PROPERTIES

Compressive strength	25 – 30 MPa
Tensile strength (UTS)	25 – 35 Mpa
Bending elastic limit (LOP)	15 – 20 Mpa
Bending strength (MOR)	50 – 65 Mpa
Youngs Modulus	5 – 6 Mpa
Impact strength (Charpy)	30 KJ/m²
Moisture movement	<1%
EN13501-1 Fire Classification	B-s1-d0
Freeze/Thaw resistance	Excellent – Test specimens undamaged
Wet/Dry 50 cycles	Test specimens undamaged

APPLICATION AREAS

Cast and laminated decorative mouldings, and with the inclusion of suitable glass reinforcements AC100 can be used for lightweight, high-impact panels. Jesmonite AC100 provides a fire resistant coating for many expanded foams for theme park and theatre props.

KEY ATTRIBUTES

Solvent free – No VOC's Good abrasion resistance and impact strength High compressive and tensile strength Rapid curing and high early strength gain

PACKAGING

Liquids are supplied in 1,5,10,20kg cannisters and base in 2.5kg bucket, 12.5 kg bucket and 25kg bag.

STORAGE

As a basic rule liquid containers should be kept well sealed to prevent water evaporation and skin forming, freezing must be avoided. They should be stored at a constant temperature between $5 - 25^{\circ}$ C and base should be kept dry and stored at $5 - 25^{\circ}$ C.

Jesmonite[®] is a Registered Trademark

The above information and recommendations are based upon our experience and are offered merely for advice. They are offered in good faith but without guarantee, as conditions and methods of use are beyond our control. It remains the responsibility of the end user to determine the suitability of the materials for the particular purpose intended.

Contact details

Jesmonite Limited Challenge Court Bishops Castle Shropshire SY9 5DW United Kingdom

Tel: +44 (0)1588 630302 Fax: +44 (0)1588 630304 www.jesmonite.com